



SUPERFLOW[®] 35 CF BRAZING ALLOY

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION:

SUPERFLOW[®] 35 CF is a cadmium free silver brazing alloy with a moderate melting range and frequently used in production brazing operations. *SUPERFLOW 35CF* is commonly used to join any combinations of copper, brass, steel, and bronze.

CHEMICAL COMPOSITION, Weight Percent:

Silver	34.0-36.0
Copper	31.0-33.0
Zinc	31.0-35.0
Total Others Elements	0.15

PHYSICAL DATA:

Solidus	1265°F (685°C)
Liquidus	1390°F (754°C)
Brazing Range	1390-1545°F (754-841°C)
Color	Yellow-gold
Specific Gravity	9.03
Density (Troy oz./cu in.)	4.90
Electrical Conductivity (% of IACS)	19.5
Electrical Resistivity (Microhm-cm)	8.18

AVAILABLE SIZES:

TAG 35CF =Troy Ounce Coils and Rods of 1/16, 3/32, 1/8
TAG 35CF = Flux coated rods of 1/16, 3/32, 1/8
Other sizes available – please inquire

SPECIFICATIONS:

AWS A5.8/A5.8M	BAG-35
ASME SFA5.8	BAG-35

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

GULF COAST
4755 Alpine Drive #100A
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.