



**W.A. ALLOY CO.**

WASHINGTON ALLOY'S Quality  
Management System is  
Certified to **ISO 9001:2008**  
Cert # 05-R0925

# 4140 Chrome-Moly Metal-Cored Wire

U.S. ALLOY CO.  
dba Washington Alloy  
7010-G Reames Rd.  
Charlotte, NC 28216  
[www.weldingwire.com](http://www.weldingwire.com)



**American Welding Society**  
Sustaining Company Member



## ALLOY DESCRIPTION AND APPLICATION:

4140MC is a metal cored wire designed for welding and build up on mild & low alloy steels having a smooth stable arc transfer, spatter free, excellent bead contour, with a high deposition rate and nearly free of slag weld bead. This wire is formulated to weld flat and horizontal which has deoxidizers that helps where mill scale may be present. This metal cored wire is typical used on dies, forgings, castings and other base metals where heat treating is required. Preheat and interpass of 500-650° F is found on AISI 4140 grades of base metal followed by slow cool and post weld heat treating to required hardness.

## TYPICAL METAL CORED WELDING PROCEDURES; DCEP

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stickout	Gas <sup>(1)</sup> (cfh)
0.035	300-650	160-315	22-34	3/8-3/4"	35-40
0.045	200-550	150-325	20-31	1/2-1"	35-45
0.052	200-575	200-440	23-33	1/2-1"	40-50
1/16"	150-470	210-480	26-35	1/2-1.25"	40-50

Procedures may vary with change in position, base metals, filler metals, equipment and other changes. <sup>(1)</sup>100 % CO<sub>2</sub> or 75% Ar/25% CO<sub>2</sub>

Hardness as welded 31-40 may be hardenable to 58

**AVAILABLE SIZES:** TU 4140MC= Spools of .045

Other sizes may be available – please inquire

**SPECIFICATIONS:** INTERNAL



2012 DC

**EAST COAST**  
7010-G Reames Rd  
Charlotte, NC 28216  
Tel (888) 522-8296  
Fax (704)598-6673

**GULF COAST**  
4755 Alpine Drive #100A  
Stafford, TX 77477  
Tel (877) 711-9274  
Fax (281)313-6332

**WEST COAST**  
8535 Utica Ave  
Rancho Cucamonga, CA 91730  
Tel(800)830-9033  
Fax (909)291-4586

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.