



WA. ALLOY CO.

WASHINGTON ALLOY'S Quality
Management System is
Certified to **ISO 9001:2008**
Cert # 05-R0925

SUPERFLOW[®] 45 CF BRAZING ALLOY

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



American Welding Society
Sustaining Company Member



ALLOY DESCRIPTION AND APPLICATION:

SUPERFLOW[®] 45 CF is a general purpose silver brazing alloy with a wide melting range and widely used in many brazing operations. *SUPERFLOW 45CF* is commonly used to join any combinations of copper, brass, steel and bronze.

CHEMICAL COMPOSITION, Weight Percent:

Silver	44.0-46.0
Copper	29.0-31.0
Zinc	23.0-27.0
Total Others Elements	0.15

PHYSICAL DATA:

Solidus	1125°F (663°C)
Liquidus	1370°F (743°C)
Brazing Range	1370-1550°F (743-843°C)
Color	Yellow White to light gold
Specific Gravity	9.11
Density (Troy oz./cu in.)	4.80
Electrical Conductivity (% of IACS)	19.0
Electrical Resistivity (Microhm-cm)	9.08

AVAILABLE SIZES:

TAG 45CF = **Troy Ounce** Coils and Rods of .030, 3/64, 1/16, 3/32, 1/8
TAG 45CF = Flux coated rods of 1/16, 3/32, 1/8
Other sizes available – please inquire

SPECIFICATIONS:

AWS A5.8/A5.8M	BAG-5
ASME SFA5.8	BAG-5
FED QQ-B-654	BAG-5

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

GULF COAST
4755 Alpine Drive #100A
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



DC 2012

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.