



WASHINGTON ALLOY'S Quality  
Management System is  
Certified to ISO 9001:2008  
Cert # 05-R0925

# 70S-6 Carbon Steel Welding Wire and Rod

U.S. ALLOY CO.  
dba Washington Alloy  
7010-G Reames Rd.  
Charlotte, NC 28216  
[www.weldingwire.com](http://www.weldingwire.com)



**American Welding Society**  
Sustaining Company Member



## ALLOY DESCRIPTION AND APPLICATION;

70S-6 is commonly a copper coated carbon steel that contains high levels of manganese and silicon for stronger deoxidizing power and has excellent welding results on mild steels where poor fit-up, rust and oils may be present.

### TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit <sup>(1)</sup> 98Ar/2O<sub>2</sub>

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Travel speed (ipm)	CO <sub>2</sub> (cfh)
0.023	80-350	30-85	14-19	10-15	20-25
0.030	110-340	40-130	15-20	12-24	20-25
0.035	100-520	60-235	16-25	11-40	20-30
0.045	70-270	90-290	18-23	12-22	25-35
<i>Spray 0.035</i>	<i>320-600</i>	<i>160-300</i>	<i>23-26</i>	<i>11-22</i>	<i>(1)25-35</i>
<i>0.045</i>	<i>170-550</i>	<i>170-375</i>	<i>23-29</i>	<i>12-21</i>	<i>(1)25-35</i>
<i>1/16"</i>	<i>175-350</i>	<i>275-475</i>	<i>25-31</i>	<i>9-19</i>	<i>(1)25-35</i>

### TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	100-160	12	3/8"	20	1/16-3/32"
1/16-3/32"	3/32"	120-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	150-300	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

### TYPICAL WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES; 100%CO<sub>2</sub>

	AWS Spec.	70S-6		AWS Spec	Typical
Carbon	0.06-0.15	0.10	Tensile Strength (psi)	70,000 min.	90,000
Manganese	1.40-1.85	1.70	Yield Strength (psi)	58,000 min.	73,000
Silicon	0.80-1.15	1.00	Elongation in 2"	22% min.	25%
Phosphorus	0.025 max.	0.010	Charpy V-notch at -20°F	20 ft-lbs min.	28 ft-lbs
Sulfur	0.035 max.	0.015	Reduction of area	n/a	60%
Copper contents and coating	0.5 max.		Average Brinell Hardness	n/a	160

**AVAILABLE SIZES:** TC 70S-6 = Spools of .023, .030, .035, .040, .045, .052, 1/16

TT 70S-6 = Cut lengths of .030, .035, .045, 1/16, 3/32, 1/8, 5/32

**SPECIFICATIONS; ANSI/AWS A5.18 ER 70S-6**

**ASME SFA 5.18 ER 70S-6**

**EAST COAST**  
7010-G Reames Rd  
Charlotte, NC 28216  
Tel (888) 522-8296  
Fax (704)598-6673

**GULF COAST**  
4755 Alpine Drive #100A  
Stafford, TX 77477  
Tel (877) 711-9274  
Fax (281)313-6332

**WEST COAST**  
8535 Utica Ave  
Rancho Cucamonga, CA 91730  
Tel(800)830-9033  
Fax (909)291-4586



DC 2012

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.