



WA. ALLOY CO.

ISO 9001:2000

SUPERFLOW BRAZING SELECTION

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



American Welding Society
Sustaining Company Member

BASE METALS	COPPER	BRASS	STEEL (NO PHOS-COPPERS)	STAINLESS NICKEL (NO PHOS-COPPERS)
COPPER	<i>SUPERFLOW PHOS-COPPERS – NO FLUX NEEDED</i> 0,2,5,6, 15 <i>SUPERFLOW SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50,50N,56	<i>SUPERFLOW PHOS-COPPERS OR HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 0,2,5,6, 15 25,30,35,38T,40,40N,40T,45,50,50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 25,30,35,38T,40,40N,40T, 45,50,50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BLACK BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50, 50N,56
BRASS	<i>SUPERFLOW PHOS-COPPERS OR HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 0,2,5,6, 15 25,30,35,38T,40,40N,40T,45,50,50N,56	<i>SUPERFLOW PHOS-COPPERS OR HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 0,2,5,6, 15 25,30,35, 38T ,40,40N,40T,45,50,50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 25,30,35,38T,40,40N,40T, 45,50,50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BLACK BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50, 50N,56
STEEL (NO PHOS-COPPERS)	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 25,30,35,38T,40,40N,40T, 45,50,50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 25,30,35,38T,40,40N,40T, 45,50,50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BRAZING FLUX</i> 25,30,35,38T,40,40N,40T, 45,50,50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BLACK BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50, 50N,56
STAINLESS NICKEL CARBIDES (NO PHOS-COPPERS)	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BLACK BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50, 50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BLACK BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50, 50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BLACK BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50, 50N,56	<i>SUPERFLOW HIGH SILVER BRAZING WITH SUPERFLOW BLACK BRAZING FLUX</i> 25,30,35,38T,40,40N,40T,45,50, 50N,56

Bold print is a good first choice—filler may change with specific requirements and design—flux coated rods may also be available



DC 11-2005

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

GULF COAST
4855 Alpine Drive #190
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.