



Quality Management System
in accordance with
ISO 9001
Cert # 05-R0925

EAGLE ARC BW-71T “T9” Carbon Steel Flux-Cored Wire

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION:

EAGLE ARC BW-71T “T9” is a baked flux cored wire designed for single or multi pass welding having a smooth arc transfer, low spatter, flat to slightly convex bead contour, with a high deposition rate and easily removal slag. This all-position baked wire has excellent feeding and low fume generation using 100% CO₂ or mixed gas making it a good choice for mild steel and higher strengths steels.

TYPICAL FCAW WELDING PROCEDURES; DCEP OPTIMUM IN BOLD (FLAT)

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stickout	CO ₂ (cfh)
0.035	275- 580 -780	130- 200 -260	23- 27 -30	3/8-3/4"	35-40
0.045	200- 450 -600	150- 250 -335	22- 29 -33	1/2-1"	35-45
0.052	150- 400 -600	140- 275 -390	19- 28 -35	1/2-1"	40-50
1/16"	150- 330 -490	150- 330 -475	23- 30 -38	1/2-1"	40-50
5/64"	120- 250 -300	250- 385 -450	26- 29 -32	3/4-1 1/4"	40-50
3/32"	110- 185 -275	300- 425 -550	25- 29 -34	3/4-1 1/4"	40-50

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WELD METAL CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec.	Eagle BW-71T “T9”		BASED ON 100% CO ₂ / MIX 75/25 IN BOLD	
Carbon	0.12 max	0.038/ 0.035		AWS Spec	Eagle BW-71T “T9”
Manganese	1.75 max	1.07/ 1.24	Tensile Strength (psi)	70-95,000	88,015 / 84,825
Silicon	0.90 max	0.41/ 0.49	Yield Strength (psi)	58,000 min.	79,460 / 75,110
Phosphorus	0.030 max.	0.012/ 0.009	Elongation in 2"	22 % min.	30.4% / 29.2 %
Sulfur	0.030 max.	0.007/ 0.007	Charpy V-notch at -20°F	20 ft·lbs min.	39.0 / 59.0 ft·lbs
Copper	0.35 max.	0.03/ 0.02			
Nickel	0.50 max.	0.01/ 0.02	Chromium	0.20 max.	0.04/ 0.03
Molybdenum	0.30 max.	0.01/ 0.01	Vanadium	0.08 max.	0.01/ 0.01

3-6-2019 Hydrogen test on Lot # of F71LFA0001191 with 100 CO₂ was @ 4.0(ml/100gl) and 75% Ar + 25% CO₂ was @ 4.1

AVAILABLE SIZES: TCB EAGLE BW-71T= Spools of .035,.045,
Other sizes available – please inquire

SPECIFICATIONS; AWS A5.20	E71T-1C/1M-9C/9M
ASME SFA 5.20	E71T-1C/1M -9C/9M
AWS A5.36	E71T1-C1[M21]A0[A2]-CS1-H8
ASME SFA 5.36	E71T1-C1[M21]A0[A2]-CS1-H8

(Formerly classified as E71T-1/-9)



EAST COAST
825 Groves St
Lowell, NC 28098
Tel (980) 550-2002
Fax (704)598-6673

GULF COAST
4855 Alpine Drive #100
Stafford, TX 77 477
Tel (888) 522-8296
Fax (281)313-6332

WEST COAST
8885 White Oak, Ste104
Rancho Cucamonga, CA 91730
Tel (888) 522-8296
Fax (909)291-4586

2-2020 DC

Warehouse Distribution Center – Dallas/Fort Worth & Portland, Oregon & Boston, Massachusetts Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.