



Quality Management System
in accordance with
ISO 9001
Cert # 05-R0925

Eagle-Arc 980X

Low Alloy High Strength Alloy Steel

Honda/Acura Approved

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION;

Honda Approved 980X is commonly a copper coated high strength alloy steel that contains high levels of nickel, manganese, silicon and molybdenum for stronger toughness and excellent welding results on fine grained high stress critical applications. Commonly found on Automotive, cranes, ships, mining, concrete pressure vessel and many other quenched and tempered steels. Used on base metals S690Q/QL/LN, S890Q/QL/LN, S906QL, S110QL, S1300QL. This **Honda Approved wire** is Excellent replacement for the Bosch DS980J which is no longer available. Honda approval date as of June 2019.

TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit 75-80Ar/20-25CO₂

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Travel speed (ipm)	(cfh)
0.030	110-340	140-230	25-32	12-24	20-35
<i>*Thin gauge setting</i>	80-220	50-180	18-22	8-20	20-30

*Consult your recommendations found in repair manuals as needed for complete repairs

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES;

	980X		980X
Carbon	0.09	Tensile Strength (psi)	150,800 min.
Manganese	1.80	Yield Strength (psi)	139,400 min.
Silicon	0.80	Elongation in 2"	15%
Nickel	2.25	Charpy V-notch at -76°F	47 ft·lbs
Molybdenum	0.55	70°F	75 ft·lbs
Chromium	0.30		
Copper contents and coating	0.50 max.		

Approved by



AVAILABLE SIZES: TC EAGLE-ARC 980X = Spools of .030

SPECIFICATIONS; AWS A5.28 ER120S-G
DIN EN ISO 16834-A , G 89 6 M21 Mn4Ni2CrMo

EAST COAST
825 Groves St
Lowell, NC 28098
Tel (888) 522-8296
Fax (909) 291-4586

GULF COAST
4855 Alpine Drive #100
Stafford, TX 77477
Tel (888) 522-8296
Fax (909) 291-4586

WEST COAST
8885 White Oak, Ste104
Rancho Cucamonga, CA 91730
Tel (888) 522-8296
Fax (909) 291-4586



Warehouse Distribution Center – Dallas/Fort Worth, Texas; Portland, Oregon ; Boston, Massachusetts ; Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part .