



CERTIFICATE of Compliance

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com

Quality Management System
in accordance with
ISO 9001:2000
Cert # 05-R0925

TRADE NAME: USA 8016-B2
Specification: AWS A 5.5 : ASME SFA 5.5
Classification: E8016-B2

Chemical Composition for Weld Metal

	AWS Requirements	Typical
Carbon (C)	0.05-0.12	0.06
Manganese (Mn)	0.90 max.	0.65
Silicon (Si)	0.60 max.	0.47
Phosphorus (P)	0.03 max.	0.011
Sulfur (S)	0.03 max.	0.009
Chromium (Cr)	1.00-1.50	1.31
Molybdenum (Mo)	0.40-0.65	0.52


Mechanical Properties for Weld Metal

	Minimum AWS Requirements	Typical ¹⁾
Tensile Strength	80,000 psi	94,000 psi
Yield Strength	67,000 psi	83,000 psi
Elongation in 2"	19 %	26 %
Charpy V-notch Impact Average	Not Specified	76 ft · lbs at -20°F

This certification is provided by Washington Alloy Co. with the expressed understanding that if the product supplied fails to conform the stated specifications, there shall be no personal liability of any kind on the undersigned and the obligation and liability of Washington Alloy Co., with respect to such non-conformance or specification failure, shall be limited to a) an obligation to furnish the purchaser, at no additional charge, material that meets the specifications and conformances or b) to refund to the purchaser the full amount of money paid to Washington Alloy Co. for the return of the product in full. In no event shall Washington Alloy Co. be liable for consequential damage.

This certifies that the product supplied will meet the requirements of the noted classification and data above. Products supplied in accordance to the Quality Management System of Washington Alloy Company.

¹⁾ STRESS RELIEVED 1 HOUR AT 1275°F


Certification Administrator

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.