



Quality Management System
in accordance with
ISO 9001
Cert # 05-R0925

E81T1-Ni1M Carbon Steel Flux-Cored Wire

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION:

81T1-Ni1M is a flux cored wire designed for single or multi pass using Argon /CO₂ shielding gas welding having a smooth spray-type transfer commonly used on low alloy steels. This all position wire normally used in applications which will produce a chemical composition of 1% nickel yielding strengths ranging from 80-100 ksi. E81T1-Ni is used extensively in the fabrication, erection and repair of structural fabrication of higher strength steels having a 70,000-80,000 psi tensile strength. The weld metal analysis of the deposit is similar to E8018-C3 low hydrogen electrodes

TYPICAL FCAW WELDING PROCEDURES; DCEP with (35-45cfh)

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stickout
0.045"	150-575	100-300	24-30	1/2-3/4"
0.052"	95-515	100-350	22-31	1/2-1"
1/16"	100-430	150-410	23-32	1/2-1"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WELD METAL (%) AND WELD METAL PROPERTIES;

	AWS Spec.	U.S. ALLOY 81T1-Ni2		AWS Spec	Typical
Carbon	0.12 max.	0.05			
Manganese	1.75 max.	1.15	Tensile Strength (psi)	80-100,000	91,200
Nickel	0.80-1.10	1.03	Yield Strength (psi)	68,000 min.	83,000
Silicon	0.80 max.	0.38	Elongation in 2"	19% min.	22%
Sulfur	0.03 max.	0.011	Charpy V-notch (-20°F)	20 ft·lbs min	48 ft·lbs
Phosphorus	0.03 max.	0.014			
Molybdenum	0.35 max.	0.22			

SPECIFICATIONS; AWS A5.20

ASME SFA 5.20

AWS A5.36

ASME SFA 5.36

E81T1-Ni1M

E81T1-Ni1M

E81T1-M21A2-Ni1

E81T1-M21A2-Ni1



EAST COAST

7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

GULF COAST

4755 Alpine Drive #100A
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST

8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586

2-2018 DC

Warehouse Distribution Center – Portland, Oregon & Boston, Massachusetts

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.