



Quality Management System
in accordance with
ISO 9001
Cert # 05-R0925

CSF-71T UNBAKED

Carbon Steel Flux-Cored Wire



CHOSUN WELDING CO., LTD.

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



American Welding Society
Sustaining Company Member

ALLOY DESCRIPTION AND APPLICATION:

CSF 71T is a UN-baked flux cored wire designed for single or multi pass welding having a smooth arc transfer, low spatter, flat to slightly convex bead contour, with a high deposition rate and easily removal slag. This all-position baked wire has excellent feeding and low fume generation using 100% CO₂ or mixed gas making it a good choice for mild steel and higher strengths steels.

TYPICAL FCAW WELDING PROCEDURES; DCEP OPTIMUM IN BOLD (FLAT)

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stickout	CO ₂ (cfh)
0.035	275- 580 -780	130- 200 -260	23-27-30	3/8-3/4"	35-40
0.045	200- 450 -600	150- 250 -335	22- 29 -33	1/2-1"	35-45
0.052	150- 400 -600	140- 275 -390	19- 28 -35	1/2-1"	40-50
1/16"	150- 330 -490	150- 330 -475	23- 30 -38	1/2-1"	40-50
5/64"	120- 250 -300	250- 385 -450	26-29-32	3/4-1 1/4"	40-50
3/32"	110- 185 -275	300- 425 -550	25- 29 -34	3/4-1 1/4"	40-50

Procedures may vary with change in position, base metals, filler metals, equipment and other changes. Use 1-2 volts less with mixed gas

TYPICAL WELD METAL CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec	CSF-71T	BASED ON 100% CO ₂ /	MIX 75/25 IN BOLD	AWS Spec	CSF-71T
Carbon	0.12 max	0.04/ 0.05				
Manganese	1.75 max	1.19/ 1.42	Tensile Strength (psi)	70-95,000	81,483 / 84,534	
Silicon	0.90 max	0.48/ 0.54	Yield Strength (psi)	58,000 min.	64,446 / 71,456	
Phosphorus	0.030 max.	0.010/ 0.011	Elongation in 2"	22 % min.	30.5% / 29.7 %	
Sulfur	0.030 max.	0.008/ 0.010	Charpy V-notch at 0°F	20 ft-lbs min.	48.3 / 39.3 ft-lbs	
Copper	0.35 max.	0.01/ 0.02				
Nickel	0.50 max.	0.01/ 0.01	Chromium	0.20 max.	0.05/ 0.04	
Molybdenum	0.30 max.	0.01/ 0.01	Vanadium	0.08 max.	0.02/ 0.01	

AVAILABLE SIZES: CSF-71T = Spools of .045, .052, 1/16" On 15#, 33# 44#

SPECIFICATIONS; AWS A5.20

E71T-1C/1M

ASME SFA 5.20

E71T-1C/1M

AWS A5.36

E71T1-C1[M21]A0-CS1-H8

ASME SFA 5.36

E71T1-C1[M21]A0-CS1-H8

(Formerly classified as E71T-1) H4 MAY ALSO BE REQUEST PRE HEAT



APPROVALS: ABS, BV, DNV GL, KR, NK, LR, BKI, CWB

EAST COAST

7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

GULF COAST

4855 Alpine Drive #100
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST

8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586

5-2019 DC

Warehouse Distribution Center – Dallas/Fort Worth, Portland, Oregon & Boston, Massachusetts Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.